



Bellofram Silicones, Inc.
a division of The Marsh Bellofram
Group of Companies

8019 Ohio River Blvd
Newell, WV 26050 USA
Ph: 304-387-1200
Fax: 304-387-1289
siliconesRFQ@bellofram.com

BMS 1-23 MOLDED CLOSED CELL SILICONE SPONGE PRODUCTS (7304-BMS)

DESCRIPTION

Bellofram Silicones 7304-BMS is a closed cell silicone sponge rubber intended for general aircraft applications. The material shall not be used with hydraulic fluids, solvents, lubricants, and fuels.

Contact us at siliconesRFQ@bellofram.com to request a free product sample or quotation.



FEATURES

- Handles temperature extremes
- Excellent gasketing material
- Low closure force
- Very low compression set
- Ultraviolet ray (UV) resistant
- Ozone resistant

MATERIAL SPECIFICATIONS

- ASTM D-1056 2D3
- BMS 1-23

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	SPECIFICATION
Compression Deflection (PSI)	ASTM D-1056	6 to 14 PSI
Corrosion	BMS 1-23	No Effect
Water Absorption	ASTM D-1056	10% MAX
Compression Set (22 Hours @ +212°F)	ASTM D-1056	35% MAX
Accelerated Aging	BMS 1-23	PASS
Elongation	ASTM D-412	150% MAX

Data noted above is based on laboratory tests and should be used as a reference only. Further information and additional specifications are available upon request. Tests, claims, representations, and descriptions regarding flammability are based on standard laboratory tests, and they may not be reliable for determining, evaluating, predicting, or describing the flammability or burning characteristics under actual fire conditions, whenever used alone or in combination with other products. Accordingly, each potential user should make an individual determination whether the flammability or burning characteristics of the product are suitable for the purpose intended by the user.